

Product Data Sheet

DIAION™ UBK08

DIAION™ UBK08 is a cation exchange resin with a uniform particle size. It has standard cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

Product

| | | |
|------------------|--------------------|--|
| Grade Name | DIAION™ UBK08 | |
| Type | Strong Acid Cation | |
| Matrix | Styrene-DVB, Gel | |
| Functional Group | Sulfonic acid | |
| Ionic Form | Na ⁺ | |

Specification

| | | |
|-------------------------|--------|-----------|
| Whole Bead Count | - | 90 min. |
| Salt Splitting Capacity | meq/mL | 2.0 min. |
| Water Content | % | 43 - 49 |
| Average Diameter | µm | 600 ± 50 |
| Uniformity Coefficient | - | 1.10 max. |

Typical Properties

| | | |
|---|------|------|
| Shipping Density | g/L | 840 |
| Particle Density | g/mL | 1.28 |
| Total Swelling (Na ⁺ to H ⁺) | % | 9 |

Recommended Operating Conditions

| | | |
|-------------------------------|-----|--|
| Maximum Operating Temperature | °C | 120 |
| Operating pH Range | | 0 - 14 |
| Minimum Bed Depth | mm | 800 |
| Service Flow Rate | m/h | 10 - 40 |
| Regenerant | | HCl H ₂ SO ₄ |
| Regenerant Concentration | % | HCl 4 - 10 H ₂ SO ₄ 1 - 4 |
| Regenerant Level | g/L | 30 - 150 |
| Regenerant Flow Rate | m/h | 2 - 10 |
| Total Rinse Requirement | BV | 2 - 10 |

Distributed by:**S.I.A.T.A Asia Pacific Pte Ltd**

37 Tannery Lane
#06-08 Tannery House
Singapore 347790
Tel: +65 6741 2994 • Fax: +65 6741 2995

www.siata.com.sg

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ UBK08 resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBK08




Fig. 2 Bed Expansion of UBK08

Distributed by:



S.I.A.T.A Asia Pacific Pte Ltd

37 Tannery Lane
 #06-08 Tannery House
 Singapore 347790
 Tel: +65 6741 2994 • Fax: +65 6741 2995

www.siata.com.sg

Operational Capacity Data




Fig. 3 Operational Capacity Data of UBK08
Regenerant : 4 % HCl

Distributed by:**S.I.A.T.A Asia Pacific Pte Ltd**

37 Tannery Lane
#06-08 Tannery House
Singapore 347790
Tel: +65 6741 2994 • Fax: +65 6741 2995

www.siata.com.sg**Notice**

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.